

Quick Panel Technical Sheet

Model	Photo	Dimension
UH122R		175.5 × 21.5mm

NO.	Property	Test Method	Test results	Remark
1	Boiling test	EN15534	Water absorption in weight: 1.10%	
2	Coefficient Linear Thermal Expansion	EN15534	$45.0 \times 10^{-6} K^{-1}$	
3	Degree of chalking	EN15534	Rating 0, no chalking	
4	Falling mass impact resistance	EN15534	Max Crack length(mm): No crack. Max Residual Indentation(mm): 0.14	
5	Formaldehyde Content	EN717-1	Non-Detected	
		ASTM D6007	Non-Detected	
6	Heavy Metal Content	EPA3051	Sb: ND, As: ND, Se: ND, Sn: ND	
7	Heat reversion	EN15534 EN479	0.11% (Test temperature: 100°C)	
8	Lead Content Test	EUNo.628/2015	Non Detected	
9	Mould resistance	ASTM G21	Rating 0	
10	Moisture Content	EN15534 EN322	0.30%	

NO.	Property	Test Method	Test results	Remark
11	Neutral salt spray test	ASTM B117	After 200 hours of tests, there was no visible change appearing on the surface: Front surface: $\Delta E^*=1.22$, Grey Scale: 4-5 Back surface: $\Delta E^*=1.06$, Grey Scale: 4-5	
		EN15534 ISO9227	$\Delta E^*=1.42$, Grey Scale=4 (Exposure 96h)	
12	Pb, Cd, Hg, Cr6+	RoHs-IEC62321	Pb: ND, Cd: ND, Hg: ND, Cr6+: ND	
13	Resistance to artificial weathering	EN15534 ISO4892-2	After 2000h exposure $\Delta E^*=1.09$, Grey Scale=4-5	
14	Swelling and water absorption (24hours immersion)	EN15534	①Swelling: 0.21% in thickness, 0.01% in width, 0.02% in length. ②Water absorption: 0.28%	
15	Swelling and water absorption (28days immersion)	EN15534	①Swelling: 0.84% in thickness, 0.03% in width, 0.02% in length. ②Water absorption: 1.69%	
16	SRI Testing	ASTM C1549, ASTM C1371, ASTM E1980	19	
17	UV Weathering test	ASTM G154	After 3000 hours test, Grey Scale 4-5, $\Delta E^*=1.42$	
18	VOC&TVOC	ASTM D5116	Non-Detected	